



Technical Specifications



Physical Properties	Test Method	Pro 3/4"	Pro 1 1/2"	Pro 2"	Pro 3"	Pro 5"
Size (in)		48" x 92"	48" x 92"	48" x 92"	48" x 92"	48" x 92"
Thickness (in)		0.75	1.5	2	3	5
Critical Fall Height Over Aggregate*	ASTM F 1292	NA	6'	9'	12'	15'
Critical Fall Height Over Concrete*	ASTM F 1292	NA	4'	6'	9'	N/A
Accessibility	ASTMF1951-14	Passed /Excellent	Passed /Excellent	Passed /Excellent	Passed /Excellent	Passed /Excellent
Water Permeability (gal/min/yd2)	ASTM F1551	59.9	59.9	59.9	59.9	59.9
Water Permeability (inches/hour)	ASTM F1551	183.7	183.7	183.7	183.7	183.7

*When tested with a system that includes synthetic turf, infill and base noted
 The provided information is, to the best of our knowledge, true and accurate (at the time of revision). This information is based on (independent) measurements and (where possible) based on average values, measured over a long and representative period. Additional information (e.g. additional characteristics, specific (independent) reports or statistical analysis) is available upon request. Polygreen Foam is allowed to change this information and/or the product (without notice) and assumes no legal responsibility for use of and/or reliance on this information.