



## Technical Specifications

Physical Properties	Test Method	Pro ¾"	Pro 1"	Pro 1½"	Pro 2"	Pro 3"
Size (in)		48" x 94"	48" x 94"	48" x 94"	48" x 94"	48" x 94"
Thickness (in)		0.75	1	1.5	2	3
Accessibility	ASTMF1951-14	Passed /Excellent	Passed /Excellent	Passed /Excellent	Passed /Excellent	Passed /Excellent
Water Permeability (gal/min/yd <sup>2</sup> )	ASTM F1551	59.9	59.9	59.9	59.9	59.9
Water Permeability (inches/hour)	ASTM F1551	183.7	183.7	183.7	183.7	183.7
Dimensional Stability	EN 13746	< 2.5	< 2.3	< 2.2	< 2.3	< 1.6

Polygreen Pro provides consistent ASTM F1292 HIC and GMAX ratings up to 17' when tested with turf and infill systems.

The provided information is, to the best of our knowledge, true and accurate (at the time of revision). This information is based on (independent) measurements and (where possible) based on average values, measured over a long and representative period. Additional information (e.g. additional characteristics, specific (independent) reports or statistical analysis) is available upon request. Polygreen Foam is allowed to change this information and/or the product (without notice) and assumes no legal responsibility for use of and/or reliance on this information.